

GRAPHICS - INK-JET DIGITAL

 Issue date : 24/02/2014
 Date last modification : 20/03/2019

4-GL3C-08457 RI-JET 75 OPTIMA GLOSS WHITE AP940 PERMANENT WK135 N
Face Material

Gloss white polymeric soft vinyl.

Type	Polymeric vinyl	
Colour and Finish	Gloss white	
Weight	100 g/m ² ±10%	ISO-536
Thickness	75 µ ±10%	ISO 534-80

Adhesive

Acrylic permanent adhesive featuring high clarity and very high cohesion. Designed for a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

Suitable for applications at low temperature

Reference	AP940 permanent	
Type	Acrylic permanent	
Min. Appl. Temp.	+5 °C	
Service Temp.	-30°C/+120°C	
Shear	Very High	
Tack	6 N/25mm	FINAT FTM9
Final Adhesion	11 N/25mm	FINAT FTM2

Liner

Type	One side siliconised clay coated Kraft	
Colour and Finish	White	
Weight	135 g/m ² ±10%	PP-032 - ISO 536
Thickness	145 µ ±10%	ISO 534
Transparency	n.a. %	DIN 53 147-64

Applications

For advertising and promotional applications (outdoor and indoor posters, billboards and signs) and for vehicle applications (flat sided including buses, trams and taxis).

- . Flammability: Self - extinguish (ISO-3795)
- . Outdoor vertical exposure durability: UP TO 5 YEARS. The Durability data are given for unprinted films only and based on Zone 1 exposure conditions (Northern and Eastern Europe, Italy, France).

Printing Methods

The RI-JET series of ink-jet print media gives excellent print results with UV, solvent and eco-solvent ink-jet printing.

Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

